





Profilfaktoren A_m/V und A_p/V in $[m^{-1}]$

Profilfaktoren für die Berechnung des Feuerwiderstandes

Facteurs de massivité A_m/V et A_p/V en $[m^{-1}]$

Facteurs utilisés en calcul de résistance au feu

UPE				
------------	---	---	---	---

UPE 80	291	341	209	258
UPE 100	278	322	204	248
UPE 120	259	298	195	233
UPE 140	247	282	187	223
UPE 160	235	267	180	212
UPE 180	225	254	173	203
UPE 200	213	240	165	193
UPE 220	198	223	155	180
UPE 240	188	211	148	171
UPE 270	178	199	142	163
UPE 300	153	171	124	141
UPE 330	138	153	113	128
UPE 360	130	144	107	121
UPE 400	120	133	100	112